

## Technical Data Sheet

### COSMETIC FOAM COVER SKIN 480/160/160 Holes 30mm & 34mm

Polyolefin's Foam Crosslinked Foams closed cells

Properties	ISO Standards	unit	CFC
<b>Density</b>	845	kg/m <sup>3</sup>	33
<b>Tensile strength</b>	1926	kPa	300
<b>Elongation Rupture</b>	1926	%	160
<b>Compressive Strength</b>	3386		
<b>deflection 25%</b>		kPa	50
<b>deflection 50%</b>		kPa	100
<b>Thermic conductivity</b>	2581		
<b>at 10°C</b>		W/mk	0.034
<b>at 40°C</b>		W/mK	0.038
<b>Using temperature</b>	internal	°C	-80/+80
<b>Water absorption</b>	internal	vol. %	
<b>after 10days</b>			
<b>Water Vapor Permeability</b>	1663	g/m <sup>2</sup> x24h	
<b>(5mn)</b>			
<b>Value μ (23°C,0-85% r.h.)</b>	1663	-	
<b>Shore Hardness 0/00</b>	internal	-	15/35
<b>Shore Hardness A</b>	internal	-	13/17

Ces informations concernant Primalux, mousses expansées, Cellules fermées, sont présumées exactes et données de bonne foi. Les résultats sont exprimés en valeurs moyennes (basés sur des épaisseurs différentes et sur la densité nominale) et doivent être considérés comme indications.

En l'absence de données statistiques, cet ensemble de résultats peut être incomplet