

PRIMALUX

**T echnical Data Sheet
PRIMALUXEV LUX**



Polyolefin's Foam Crosslinked Foams closed cells

Properties	ISO Standards	unit	LUX
Density	845	kg/m ³	140
Tensile strength	1926	kPa	1550
Elongation Rupture	1926	%	285
Compressive Strength deflection 25% deflection 50%	3386	kPa kPa	190 280
Thermic conductivity at 10°C at 40°C	2581	W/Mk W/mK	
Using temperature	internal	°C	-80/+60
Thermoforming temperature	internal	°C	±100
Water absorption after 10days	internal	vol.%	
Water Vapor Permeability (5mn)	1663	g/m ² x24h	
Value µ (23°C,0-85% r.h.)	1663	-	
Shore Hardness 0/00	internal	-	
Shore Hardness A	internal	-	32/37

Ces informations concernant Primalux, mousse expansées, cellules fermées, sont présumées exactes et données de cet ensemble de résultats peut être bonne foi. Les résultats sont exprimés en valeurs moyennes (basés sur des épaisseurs différentes et sur la densité nominale) et doivent être considérés comme indications.

En l'absence de données statistiques, incomplet